



CO-ORDINATION OF NOTIFIED BODIES
PPE-Directive 89/686/EEC + amendments

CNB/P/ 08.036
Revision 00
Language: E

RECOMMENDATION FOR USE

Number of pages: 1	Date: 19.09.16	Approval by :	Approved on :
Origin : VG8		<input checked="" type="checkbox"/> Vertical Group	05.10.16
		<input checked="" type="checkbox"/> Horizontal Committee	09.01.17
		<input checked="" type="checkbox"/> Standing Committee	(date)
Question related to: Directive 89/686/EEC	EN/prEN: EN ISO 15027-1:2012 & EN ISO 15027-2:2012	Other:	
Annex:	Article: 10	Clause: 4.12	
Key words: Preconditioning of immersion suit material samples			
Question: In ISO 15027 for immersion suit samples the temperature cycling and rotating shock bin test be carried out first prior to all other tests but does this also apply to the material samples too when performing the tests from clause 4.12?			
Solution: Yes All material samples must go through the temperature cycling test as a preconditioning to all the individual material tests in clause 4.12, but the rotating shock bin test is not applicable for the material samples.			
Sent to: <input checked="" type="checkbox"/> members of the VG <input type="checkbox"/> other(s) VG <input checked="" type="checkbox"/> HC (2) <input type="checkbox"/> TC (3) <input type="checkbox"/> SC (4) <input type="checkbox"/> other (5)			
(5)			

(1) Essential safety requirement
(2) HC = horizontal committee

(3) N° of CEN/TC (Secretary & Chairman)
(4) EEC Standing Committee 89/392

(5) To be specified