



**CO-ORDINATION OF NOTIFIED BODIES
PPE-Directive 89/686/EEC + amendments**

CNB/P/10.023
Revision 02
Language: E

RECOMMENDATION FOR USE

Number of pages: 1	Date: 22/01/97	Approval by :	Approved on :
Origin: Horizontal Committee		<input checked="" type="checkbox"/> Vertical Group	22/01/97
		<input checked="" type="checkbox"/> Horizontal Committee	13/09/11
		<input type="checkbox"/> Standing Committee	
Question related to:	EN/prEN:	Other:	
Annex:	Article:	Clause:	
Key words: Hydrolysis of outsoles			
Question: If an outsole consists of several layers, e.g. a rubber and a polyurethane layer, is it necessary to perform the hydrolysis test procedure according to EN 344, section 4.8.6?			
Solution: Testing according to EN 344, section 4.8.6, is to be done in the case that the outer layer of the outsole consists of polyurethane. In all other cases the test is not necessary.			
Sent to: <input checked="" type="checkbox"/> members of the VG <input type="checkbox"/> other(s) VG <input checked="" type="checkbox"/> HC (2) <input checked="" type="checkbox"/> TC (3) <input type="checkbox"/> SC (4) <input type="checkbox"/> other (5)			

(1) Essential safety requirement
(2) HC = horizontal committee

(3) N° of CEN/TC (Secretary & Chairman)
(4) EEC Standing Committee 89/392

(5) To be specified