



**CO-ORDINATION OF NOTIFIED BODIES  
PPE-Directive 89/686/EEC + amendments**

CNB/P/10.077  
Revision 01  
Language: E

**RECOMMENDATION FOR USE**

Number of pages: 1	Date: 10/11/03	Approval by :	Approved on :
Origin: SATRA		<input checked="" type="checkbox"/> Vertical Group	04/03/04
		<input checked="" type="checkbox"/> Horizontal Committee	13/09/11
		<input type="checkbox"/> Standing Committee	
Question related to: Directive 89/686/EEC	EN/prEN: ISO 20345 etc...	Other:	
Annex:	Article:	Clause:	
Key words: Leather upper test			
Question: In the EN ISO 20345  Table 9 upper leather / textile are tested for the tear resistance Table 10 upper leather (crust) / rubber / polymer are tested for the tensile property  1. Why leather is tested 2 times? 2. Does that mean that a full grain leather is not tested for the tensile property? yes 3. Does that mean that a upper leather (crust)is not tested for the tear resistance? no			
Solution: 1. leather is tested 2 times for historical reasons. 2. a full grain leather is not tested for the tensile property. 3. a upper leather (crust) shall be tested for the tear resistance.			
Sent to: <input checked="" type="checkbox"/> members of the VG <input type="checkbox"/> other(s) VG <input checked="" type="checkbox"/> HC (2) <input checked="" type="checkbox"/> TC (3) <input type="checkbox"/> SC (4) <input type="checkbox"/> other (5)			

(1) Essential safety requirement  
(2) HC = horizontal committee

(3) N° of CEN/TC (Secretary & Chairman)  
(4) EEC Standing Committee 89/392

(5) To be specified