



CO-ORDINATION OF NOTIFIED BODIES
PPE-Directive 89/686/EEC + amendments

CNB/P/10.100
Revision 01
Language: E

RECOMMENDATION FOR USE

Number of pages: 1	Date: 25/04/06	Approval by :	Approved on :
Origin: INESCOP		<input checked="" type="checkbox"/> Vertical Group	24/03/06
		<input checked="" type="checkbox"/> Horizontal Committee	13/09/11
		<input type="checkbox"/> Standing Committee	
Question related to: Assessment of damage	Annex:	Article:	EN ISO 20344,5,6,7
		Clause:	Other:
Key words: Heat insulation / sand bath			
Question: EN ISO 20344, 5.12.3 says that it must be reported any damage which can seriously affect the functionality of the footwear. EN ISO 20345,6.2.3.1 says that there shall be no distortion or embrittlement of the sole that reduces its functionality.			
Solution: (a) If cleats collapse or clear signs of melting or any separation of layers = FAIL (b) If no signs of visible damage = PASS (c) If not sure about level of damage = Carry out abrasion resistance test using heat insulation sample and the results must be below 150mm ³ to be considered as a PASS result.			
Sent to: <input checked="" type="checkbox"/> members of the VG <input type="checkbox"/> other(s) VG <input type="checkbox"/> HC (2) <input checked="" type="checkbox"/> TC (3) <input type="checkbox"/> SC (4) <input type="checkbox"/> other (5)			

(1) Essential safety requirement
(2) HC = horizontal committee

(3) N° of CEN/TC (Secretary & Chairman)
(4) EEC Standing Committee 89/392

(5) To be specified