



CO-ORDINATION OF NOTIFIED BODIES
PPE-Directive 89/686/EEC + amendments

CNB/P/10.143
Revision 01
Language: E

RECOMMENDATION FOR USE

Number of pages: 1	Date: 30/04/2010	Approval by :	Approved on :
Origin: INESCOP		<input checked="" type="checkbox"/> Vertical Group	30/04/2010
		<input checked="" type="checkbox"/> Horizontal Committee	13/09/2011
		<input type="checkbox"/> Standing Committee	
Question related to: Insole abrasion resistance	EN ISO 20344/5/6/7	Other:	
Annex:	Article:	Clause:	
Key words: Sock lining, insole abrasion			
Question: The abrasion resistance of the insole must be carried out according to EN ISO 20344 Clause 7.3. However, when the footwear has an inner sock lining covering also the insole that method seems to be meaningless. For textiles the Martindale method (Clause 6.12), used for linings and insocks is more adequate.			
Solution: When footwear has an inner sock lining it is enough to carry out the abrasion resistance of the lining according to clause 6.12 and is unnecessary to carry out the insole abrasion test according to Clause 7.3.			
Sent to: <input checked="" type="checkbox"/> members of the VG <input type="checkbox"/> other(s) VG <input checked="" type="checkbox"/> HC (2) <input checked="" type="checkbox"/> TC (3) <input type="checkbox"/> SC (4) <input type="checkbox"/> other (5)			

(1) Essential safety requirement
(2) HC = horizontal committee

(3) N° of CEN/TC (Secretary & Chairman)
(4) EEC Standing Committee 89/392

(5) To be specified